

**GENERAL FEATURES**

This thermosetting powder with epoxy and polyester resins is suggested for polymerisation at low temperature (160°C).  
 The product forms a level hard film with good resistance to mechanical damage, detergents, fuels and oils. It has good resistance to yellowing caused by the chain stop during stoving.  
 The product has good chemical resistance.

**APPLICATION**

Due to its special content the product has excellent protective and decorative effects. It is particularly suggested for interior coating.

**ADVISED CYCLES**

The surface to be coated must be cleaned from oils, grease or flash rust.  
 If particular resistance to corrosion or humidity is required, it is suggested the following pretreatment of the surface:

for steel	sand blasting or/and iron or zinc phosphatising
for galvanised steel and aluminium	chromatising

**HANDLING AND STORAGE**

Store at temperatures lower than 30°C; higher temperatures may damage the powder by causing undesired alterations or blobs.  
 Storage life in original package: 12 months.

**TECHNICAL DATA**

Code	Int. Method	Range	Ref. Method
P/CL092	Calc. specific gravity(kg/l):	1.25 - 1.650	
P/YC060	Particle size dist. >32µ(%):	36 - 46	
P/YC120	Particle size dist. >63µ(%):	74 - 91	
P/CL143	1µm Theor. spread rate (m2/kg):	540 - 780	

**WAYS OF APPLICATION**

Apply with guns with negative terminal (60/80KV) or triboelectric guns automatically or manually.  
 It is advised to apply the product in layers with the thickness of 60-80 microns and to stove at 170°C for 15 minutes.  
 For stoving the epoxy polyester BT glossy products it is possible to use the following combinations of time and temperature:

10-15 minutes	180°C (temperature of the support)
15-22 minutes	170°C (temperature of the support)
20-30 minutes	160°C (temperature of the support)

For stoving use the given indications.

**TECHNOLOGICAL FEATURES AND RESISTANCE TESTS**

The support used	UNI sheet
Thickness	60 microns
Stoving	15 minutes at 170°C
Appearance and levelling	good

The hardness test was carried out on zinc phosphatised steel.

Code	Int. Method	Range	Ref. Method
P/CC050	Gloss 60° :	85 - 95.0	UNI EN ISO 2813:2001
P/CM010	Buchholz indentation test :	more than 90	UNI EN ISO 2815
P/CM181	Pendulum-rocker hardness : Persoz pendulum	more than 300	UNI 8402
P/CM040	Erichsen cupping test (mm):	more than 3	UNI EN ISO 1520
P/CM050	Direct impact test (cm.Kg):	more than 20	UNI 8901
P/CM051	Opposite impact test(cm.kg):	more than 5	UNI 8901
P/CM170	Conical mandrel : Bend test	maximum 20 mm	UNI EN ISO 6860
P/CM100	Crosscut adhesion (2mm)(GT):	00	UNI EN ISO 2409
P/CM190	Salt fog test :	1000 hours later - indentation along the cross of 3-6 mm	UNI ISO 9227
P/CM230	Resistance to humidity : (Humidity test)	500 hours later - no change	UNI 8744

Our technical data sheets represent the results of the lab tests; they do not have binding value.