

EPOXY THERMOSETTING POWDER COATING FOR INDOOR USE

**Product
fundamental
characteristics**

ST Epoxy powder coatings are based on high quality raw materials conveniently chosen to give the finishing excellent resistance to chemical agents and good mechanical properties.

Cure cycle

From 140°C x 20' to 200°C x 20' according to the required reactivity.

Gloss

According to the required finishing, the gloss of **ST Epoxy** powder coatings can be chosen inside the range 5 - 95 units (value determined at 60°).

Coverage

The theoretical coverage of ST powder coatings is calculated according to this formula:
 $Coverage (m^2) = 1000 / (S \times G)$
 Where S is the coating thickness in microns and G the specific weight of the powder.

Application

According to the customer's specific needs, **ST Epoxy** powder coatings can be formulated particularly for the following application systems:

- Corona;
- Tribo;
- Fluid bed.

**Substrate
preparation**

Before the painting, the item should be adequately pre-treated in accordance with surface type, final use and required performances. The following table can be used as starting point for the pre-treatment choice

Substrate	Indoor use	Outdoor use	Architecture
Aluminium	Soil removal, Chromate, Chrome-Free	-	-
Steel	Soil removal, Iron Phosphate, Zinc Phosphate, Sand-blasting	-	-
Zinc coated steel	Acid attack, Iron Phosphate, Zinc Phosphate, Chromate	-	-

**Particle size
distribution**

ST Epoxy powder coatings are characterized by an average particle size between 30 and 40 microns. According to the customer's specific needs, specific particle size distributions can be supplied.

Typical applications	<p>ST Epoxy powder coatings can be used for painting several products for indoor use where high resistance to chemical agents is required. Typical applications include:</p> <ul style="list-style-type: none"> • Electrical cabinets • Lighting plants • Shelves • Domestic items • Piping • Wheels • Toys • Fire-extinguishers
-----------------------------	---

Storage stability	<p>ST Epoxy powder coatings are stable for at least 6 months if stored in a dry place, at temperatures below 30°C.</p>
--------------------------	---

General properties of the series ⁽¹⁾	Regulation	Test result
Impact Test ⁽²⁾	ASTM D2794	2,5 Nm
Adhesion ⁽²⁾	ISO 2409	GT0
Cupping test ⁽²⁾	ISO 1520	5 mm
Bending test ⁽²⁾	ISO 1519	5 mm
Salt spray ⁽³⁾	ISO 9227	1000 hours without film separation
Humidity test ⁽³⁾	DIN 50017	1000 hours without film separation or blistering
Acetone	100 double passages with cotton wad	● Limited resistance
Ethyl alcohol	100 double passages with cotton wad	↑ Excellent resistance
Methylethylketone	100 double passages with cotton wad	● Limited resistance
Perchloroethane	100 double passages with cotton wad	● Limited resistance
Toluene	100 double passages with cotton wad	↑ Excellent resistance
Trichloroethane	100 double passages with cotton wad	● Limited resistance
Xylene	100 double passages with cotton wad	↑ Excellent resistance
Acetic acid	Film immersion for 30 days	↑ Excellent resistance
Citric acid	Film immersion for 30 days	● Limited resistance
Hydrochloric acid	Film immersion for 30 days	↑ Excellent resistance
Phosphoric acid	Film immersion for 30 days	↑ Excellent resistance
Lactic acid	Film immersion for 30 days	↑ Excellent resistance
Sulphuric acid	Film immersion for 30 days	↑ Excellent resistance
Ammonium hydroxide	Film immersion for 30 days	↑ Excellent resistance
Sodium hydroxide	Film immersion for 30 days	↑ Excellent resistance

⁽¹⁾ All tests have been carried out on smooth glossy finishes.

⁽²⁾ Tests carried out on Unichim steel panels with coating thickness of about 60 microns.

⁽³⁾ Tests carried out on Bonder 26S/60/0C panels with coating thickness of about 60 microns.

Note

The information given in this Technical Data Sheet, based upon laboratory tests, is currently correct to the best of our knowledge. Since product application and conditions vary and are often beyond our control, we can guarantee only the product quality itself. In the light of continuous product improvement, ST Powder Coatings reserves the right to modify without notice the content of this technical sheet.

Edition: 1

Date: 11-04-2005